



A Division of R&P Inc.

## Black 220 Hot Tar & Asphalt

Phone (503) 289-7720 Fax (503) 289-8920 Toll Free (800) 234-2358

**Application:** A heat and oil resistant compound designed to operate in applications requiring resistance to high temperatures and oil. Recommended for hot mixtures containing diesel oil as well as kerosene, petroleum coke, hot asphalt paving mixes and carbon pitch, ect. Hot service involving petroleum oils such as oil extractors and plants handling oily grains or seeds where the belt will be subject to vegetable oils, high temperature and moisture from steam [Caution: This compound often does not work well in hot applications where oil is not present]

### Technical Data

	Imperial
Working Tension	220
Number Of Plies	2
Fabric Type	Poly/Nylon
Top Surface	3/16"
Bottom Surface	1/16"
Overall Gauge	3/8"
Weight (Per Inch of Width)	.230
Minimum Rec. Pulley Diameters	10"
Working Temperature	-30/350 F

### Splicing Methods

Vulcanized	Plate	Hinged	Hinged
Bias	140/190	375/550	R5

\* Fastener manufacturer should be consulted to review belt and application information.

No warranty, including implied warranty of merchantability, fitness for a particular purpose, or other warranty of quality is either expressed or implied of this product. The information on this specification sheet supercedes all previously printed material.